



6×26WS+IWRC



6×31WS+IWRC



6×36WS+IWRC

Nominal diameter mm	Approx Weight kg/100m	Nominal Strength Mpa				
		1570	1670	1770	1870	1970
		Min. Breaking Load kN				
8	26.8	35.8	38.0	40.3	42.6	44.7
10	41.8	55.9	59.5	63.0	66.6	69.8
12	60.2	80.5	85.6	90.7	95.9	100
13	70.6	94.5	100	106	113	118
14	81.9	110	117	124	130	137
16	107	143	152	161	170	179
18	135	181	193	204	216	226
20	167	224	238	252	266	279
22	202	271	288	305	322	338
24	241	322	342	363	383	402
26	283	378	402	426	450	472
28	328	438	466	494	522	547
30	376	503	535	567	599	628
32	428	572	609	645	682	715
34	483	646	687	728	770	807
36	542	724	770	817	863	904
38	604	807	858	910	961	1010
40	669	894	951	1010	1070	1120
42	737	986	1050	1110	1170	1230
44	809	1080	1150	1220	1290	1350
46	884	1180	1260	1330	1410	1480
48	963	1290	1370	1450	1530	1610
50	1040	1400	1490	1580	1660	1740
52	1130	1510	1610	1700	1800	1890
54	1220	1630	1730	1840	1940	2030
56	1310	1750	1860	1980	2090	2190
58	1410	1880	2000	2120	2240	2350
60	1500	2010	2140	2270	2400	2510

Note: The total Min. breaking load=Min. breaking load X 1.321 (steel core)